

Technical Data Sheet

GEHR Noryl-30GF[®]



I. Physical Properties

	Test method	Unit	Value
1. Specific gravity	ASTM D792	g/cm ³	1.31
2.a Water Absorption (saturation)	ASTM D570	%	-
2.b Humidity Absorption (saturation)			0.06
3.a Maximum permissible service temp.	UL 746B	°F	230
3.b Lower permissible service temp.			-

II. Mechanical Properties

1. Tensile strength at yield	ASTM D638	psi	-
2. Tensile Modulus		-	
3. Elongation at yield		%	-
4. Tensile strength at break		psi	17,500
5. Elongation at break		%	5
6. Impact strength	ASTM D256	ft-lb/in	-
7. Notch impact strength		ft-lb/in	2.2
8. Ball indentation / Rockwell hardness	ASTM D785	R-Scale	108
9. Shore-D	ASTM D2240	-	89
10. Flexural strength	ASTM D790	psi	25,000
11. Flexural Modulus			1,130,000

III. Thermal Properties

1. Vicat-softening point	VST/B/50	ASTM D1525	°F	289
	VST/A/50			-
2. Heat deflection temperature	HDT/B (66 psi)	ASTM D648	°F	285
	HDT/A (264 psi)			275
3. Coefficient of linear thermal expansion		ASTM D696	in/in/°F *10 ⁻⁵	1.4
4. Thermal conductivity at 73 °F		ASTM C177	BTU/hr-ft*°F	-
5. Glass transition temperature		ASTM D3418	°F	280
6. Melting temperature				280

IV. Electrical Properties

1. Volume resistivity	ASTM D257	Ω*cm	≥10 ¹³
2. Surface resistivity		Ω	≥10 ¹³
3. Dielectric constant at 1MHz	ASTM D150	-	-
4. Dielectric loss factor at 1 MHz		-	-
5. Dielectric strength	ASTM D149	V/mil	530
6. Tracking resistance	IEC 60112	Grade	-

V. Additional Data

1. Bondability	-	-	yes
2. Compliances ⁸⁾	FDA	-	no
	NSF	-	61
3. Flammability ⁸⁾	UL 94	-	V-1
4. Limited Oxygen Index (LOI)	ASTM D2863	%	26
4. UV stabilization	-	-	limited

⁸⁾ tested only for natural colored material

All values are attributes of the used raw materials.

The physical data contained in this table are typical values. They are obtained on test specimens under specific conditions and represent average values of a large number of tests. The results obtained on this tests specimens cannot be applied to finished parts without reservations, as behavior is influenced by processing and shaping. Reproduction only with our definite permission.